



# SAF30 5 SA

## TWO-COMPONENT METHYL METHACRYLATE

### KEY FEATURES

- Short open and fixture times, cure time of approximately 5 minutes
- Non-sag application on vertical surfaces
- Excellent environmental resistance

### DESCRIPTION

Designed with patented methyl methacrylate technology, Bostik's SAF structural adhesive product line offers unmatched chemical, environmental, mechanical and fatigue resistance for many industrial applications. Able to bond a wide range of dissimilar substrates, including composites, metals and plastics, the SAF product line features high elongation from 30-250%, smart viscosity formulation, minimal surface preparation and a wide range of open and curing times.

### RANGE OF APPLICATION

The SAF30 5 SA is recommended for the following substrates:

METALS	COMPOSITES	PLASTICS
Steel	Polyester	PVC
Stainless Steel	Vinyl ester	PS
Aluminum	Epoxy	ABS
	Acrylic (Elium)	PC
		PMMA

### PRODUCT CHARACTERISTICS

#### CURING PROPERTIES

Properties	Result
System	Two-component 10:1 volume ratio
Polymerization	Room temperature



### TYPICAL PHYSICAL PROPERTIES

Properties	Resin	Hardener Bostik SAF D
Appearance	Off-White	White
Density ( $\pm$ 0.02)	1.08	1.16
Viscosity @77°F (23°C)	300,000 - 600,000 <sup>1</sup>	50,000 - 180,000 <sup>2</sup>
Type	Non-sag	

### CURING PROPERTIES

Properties	Result
Open time [min]	3 - 5
Fixture time @77°F (23°C) [min]	5 - 9
Full cure [hours]	24

### MECHANICAL PROPERTIES

Properties	Result
Lap shear strength [MPa/psi] <sup>3</sup> thickness 250µm	16 - 18 / 2,320 - 2,611 CF <sup>5</sup>
Tensile strength at break [MPa/psi] <sup>3</sup>	11 - 13 / 1,595 - 1,885
Tensile modulus [MPa/psi] <sup>3</sup>	700 - 900 / 101,526 - 130,534
Hardness [Shore D]	70 - 80
Elongation at break <sup>4</sup>	20% - 30%

## WEATHERING AND AGING RESISTANCE

Lap shear strength (MPa/psi with ISO 4587 after D3 cycle.  
D3 cycle: NF EN ISO 9142, 7 aging cycles (7 days).  
CH7: Humid Cataplast, 7 days.

LAP SHEAR STRENGTH (MPa/psi) <sup>3</sup> THICKNESS 250µm			
Substrates	Before aging cycles	After aging cycles D3	After aging cycles CH7
Aluminum 6060	17 / 2,466 CF <sup>5</sup>	16 / 2,321 CF	10 / 1,450 CF
Stainless steel	16 / 2,321 CF	14 / 2,031 CF	10 / 1,450 CF
FPR	DF <sup>6</sup>	DF	DF

### NOTE

<sup>1</sup> Brookfield viscosity (mPa.s) mobile T-F @ 10 rpm

<sup>2</sup> Brookfield viscosity (mPa.s) mobile RV7 @ 10 rpm

<sup>3</sup> ISO 4587

<sup>4</sup> ISO 527-1A

<sup>5</sup> CF: Cohesive Failure

<sup>6</sup> DF: Delamination Failure

## SURFACE PREPARATION

Use an appropriate cleaning agent, such as isopropyl alcohol, to remove grease, contamination or poorly adhering oxides from metal surfaces. Most plastics require a simple cleaning before bonding. Some may require sanding for better performances.

## PRECAUTIONS

Adhesive contains methacrylate monomers and is flammable. Materials must be stored in cool place away from sources of heat. During the polymerization, the chemical reaction causes a typical smell; please use the product in a well-ventilated area.

When the adhesive's two components are mixed, an exothermic reaction can occur and generates heat. The amount of heat is dependent on the mass and thickness of the mixed product.

Read material Safety Data Sheet before handling or using this product.

## APPLICATION

The optimum quality is obtained at room temperature, ideally between 64 – 82°F (18 – 28°C) without post-curing.

Follow the instructions on the product operating guide or contact your Bostik representative for any information concerning product use or dispensing equipment.

## STORAGE AND SHELF LIFE

The SAF30 5 SA shelf life is 9 months in unopened original packaging. The product may be stored in a closed container in a dry place at temperature between 59 – 77°F (15 – 25°C).

Exposure to higher or lower temperature will result in a reduction of the stated shelf life.

## PACKAGING

For packaging information please call your Bostik sales or technical representative.

## LIMITED WARRANTY


Limited Warranty found at [www.bostik.com/us](http://www.bostik.com/us) or call 800.726.7845. TO THE MAXIMUM EXTENT ALLOWED BY LAW, BOSTIK DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING WITHOUT LIMITATION WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. UNLESS OTHERWISE STATED IN THE LIMITED WARRANTY, THE SOLE REMEDY FOR BREACH OF WARRANTY IS REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. BOSTIK DISCLAIMS ANY LIABILITY FOR DIRECT, INCIDENTAL, CONSEQUENTIAL, OR SPECIAL DAMAGES TO THE MAXIMUM EXTENT ALLOWED BY LAW. DISCLAIMERS OF IMPLIED WARRANTIES MAY NOT BE APPLICABLE TO CERTAIN CLASSES OF BUYERS AND SOME STATES DO NOT ALLOW THE EXCLUSION OR LIMITATION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE ABOVE LIMITATIONS MAY NOT APPLY TO YOU. The information, data, and recommendations made herein are based on Bostik's research only and are not guaranteed to be accurate. The performance of the product, its shelf life, and application characteristics will depend on many variables, including but not limited to the kind of materials to which the product will be applied, the environment in which the product is stored or applied, and the equipment used for application. Any change in any of these variables can affect the product's performance. Bostik does not warrant the product's suitability for any particular application. It is the buyer's obligation to test the suitability of the product for an intended use prior to using it. The Limited Warranty extends only to the original purchaser and is not transferable or assignable. Any claim for a defective product must be filed within 30 days of discovery of a problem, and must be submitted with written proof of purchase.

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### BOSTIK HOTLINE

Smart help  
1-800-726-7845

Bostik, Inc.  
11320 W Watertown Plank Road  
Wauwatosa, WI 53226  
[www.bostik.com/us](http://www.bostik.com/us)



This document supersedes all previously published literature.  
09.05.19